



Images Description and Claims (10 Kb)

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT  
COOPERATION TREATY (PCT)

(11) WO 99/64353

(13) A1

(21) PCT/IB98/01431

(22) 08 July 1998 (08.07.1998)

(25) Russian

(26) Russian

(30) 98063031

11 June 1998  
(11.06.1998)

UA

(43) 16 December 1999 (16.12.1999)

(51)<sup>6</sup> C01B 31/06, C30B 29/04

(54) HETEROGENEOUS LIQUID-PHASE CRYSTALLISATION OF DIAMOND

(71) **SEREDA, Anatoly Pavlovich** [UA/UA]; ul. Andreyva Ivanova, 21/17-33,

(72) **Kiev-010**, 252010 (UA). **DYADENKO, Arkadi Igorevich** [UA/UA]; ul.  
Heroev Sevastopolya, 24/2-10, Kiev-065, 252065 (UA).

(81) AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK,  
EE, ES, FI, GB, GE, GH, GM, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC,  
LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO,  
RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW

(84) ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent  
(AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY,  
DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF,  
BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG)

**Published**

-- with international search report

(57) The present invention relates to a principle for the heterogeneous liquid-phase crystallisation of diamond, wherein said crystallisation is carried out on the heterogeneous surface of a catalyst. This surface is characterised in that, during the high-temperature dehydrogenation process of heavy hydrocarbons containing bitumen-tar and asphaltenes, the catalyst performs a chemisorption of hydrogen under an atomic form. The catalyst surface submitted to the chemisorption exhibits a characteristic which is essential for the crystallisation of diamond in that only the growth of crystalline carbon-diamond is possible. This invention also relates to a method for implementing this principle with a yield in excess of 3,000 carats of diamond crystals having various fractions of between 100 and 1000 microns. During the experiments, the largest diamond crystal obtained had dimensions of 3.5 x 3.5 mm, while the production of diamond crystals with maximal dimensions was not contemplated as a goal.